

**BLACK POLYETHYLENE MASTERBATCH FOR
FILM, EXTRUSION AND COMPOUNDING**



PLASBLAK® PE1371



PLASBLAK® PE1371 is designed for high quality packaging film and agricultural film, requiring maximum protection against UV light degradation. It can also be used in general extrusion, moulding and cable sheathing applications.

This product is suitable for use in a wide range of plastics that come into contact with food. For more details regarding the food contact compliance in various European countries, please refer to the relevant Food Contact Statement that you can obtain through your usual Cabot representative.

METHOD OF ADDITION

PLASBLAK® PE1371 is designed for ease of dilution and homogeneous mixing and is therefore suitable for direct addition using automatic dosing units or by pre-blending.

ADDITION RATE

The amount of masterbatch added depends on the performance requirements of the final application. Typical addition rates vary from 2% to 7% masterbatch.



Cabot Corporation
www.cabot-corp.com/plastics

PHYSICAL PROPERTIES

PROPERTY	VALUE	TEST METHOD (*)
Carrier	LDPE	
Pigment	40% P-type carbon black	
Compatibility	LDPE, LLDPE, HDPE, PP, ethylene copolymers	
Density @ 23°C	1140 kg/m ³	CTM E023
MFI 21.6 kg/190°C	22 g/10 min	CTM E005 (ISO 1133)

(*) Tests are performed according to Cabot Test Methods (CTM) based on international Standards

Impact on physical properties of LDPE

Influence of a 6.25% addition of PLASBLAK® PE1371 (2.5% carbon black) in natural LDPE

Property	Test method	Unit	Natural LDPE	LDPE + 6.25% PE1371
Density @23°C	CTM E023	kg/m ³	925	934
Vicat softening point	ISO 306	°C	94	93
MFI 2.16 kg/190°C	CTM E005 (ISO 1133)	g/10 min	2.3	2.4
Tensile strength at break	ISO R527	MPa	15.1	14.7
Tensile strength at yield	ISO R527	MPa	10.3	10.9
Elongation at break	ISO R527	%	530	530

Quoted test results should not be used for specification purposes but are typical values intended for guidance only.

PACKAGING

PLASBLAK® PE1371 is supplied in regular pellet form packed in 25 kg bags. It should be stored in a dry place. It can also be supplied in micropulverised form under code PM1371. Recommended storage life: up to 1 year provided it is stored as directed.

04-12-2006

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and CABOT DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AS TO (i) SUCH INFORMATION, (ii) ANY PRODUCT OR (iii) INTELLECTUAL PROPERTY INFRINGEMENT. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.

HEAD OFFICE Cabot SCCC Interleuvenlaan 15 I B - 3001 Leuven - Belgium Tel : +32 16 39 24 00 Fax : +32 16 39 24 44	Cabot Plastics Belgium S.A. Rue Prevochamps 78 B - 4860 Pepinster - Belgium Tel: +32 87 39 27 11 Fax: +32 87 46 98 69	Cabot Plastics Deutschland Tel: (0800) 182 40 86 Fax: (0800) 182 40 87 c/o Cabot Plastics Belgium S.A. (see address on the left)	中国 卡博特(中国)投资有限公司 中国上海吴泾双柏路558号 邮编:201108 电话:+86 21 6434-7766 传真:+86 21 6434-5532
SALES OFFICES Cabot Plastics Hong Kong Ltd 18 Dai Kwai Street Tai Po Industrial Estate / NT Hong Kong SAR - PRC Tel: +852 2666 2666 Fax: +852 2666 0807	Cabot Latin America Division Rua do Paraíso, 148 – 5th floor Paraíso CEP 04103-000 São Paulo SP - Brazil Tel: +55 11 21 44 64 00 Fax: +55 11 32 53 00 51 Tel.: (0800) 195 959 (Customer Service)	Cabot Italiana S.p.A Zona Industriale, 4 I - 38055 Grigno (TN) - Italia Tel: +39 0461 775 211 Fax: +39 0461 765 146	

PLASBLAK®, PLASWITE®, PLASGREY®, PLASADD®, CABELLEC® and CABOT® are registered trademarks of Cabot Corporation
 © Cabot Corporation, MA, U.S.A. All rights reserved. 2010