

BLACK POLYETHYLENE MASTERBATCH FOR
FILM, SHEET EXTRUSION, GEOMEMBRANES
AND MOULDING APPLICATIONS



PLASBLAK® PE2272

PLASBLAK® PE2272 is designed for general purpose film and geomembranes, sheet extrusion and moulding applications.

NOTE: Two versions of this grade exist: PE2272 which is not REACH compliant and PE2272R which is manufactured to comply with REACH legislation within Europe. If the REACH compliant version is required, it should be ordered under the reference PE2272R.

METHOD OF ADDITION

PLASBLAK® PE2272 is designed for ease of dilution and homogeneous mixing and is therefore suitable for direct addition using automatic dosing units or by pre-blending.

ADDITION RATE

The amount of masterbatch added depends on the performance requirements of the final application and the carbon black content specified in the finished product. Typical addition rates vary from 2% to 5% masterbatch (8% to 25% in mulch film).



Cabot Corporation
www.cabot-corp.com/plastics

PLASBLAK® PE2272

BLACK POLYETHYLENE
MASTERBATCH FOR FILM, SHEET
EXTRUSION, GEOMEMBRANES AND
MOULDING APPLICATIONS



PHYSICAL PROPERTIES

PROPERTY	VALUE	TEST METHOD (*)
Carrier	PE	
Pigment	50% SRF carbon black	
Compatibility	LDPE, LLDPE, HDPE, PP, ethylene copolymers	
Density @ 23°C	1230 kg/m3	CTM E023
MFI 10 kg/190°C	13 g/10 min	CTM E005 (ISO 1133)

(*) Tests are performed according to Cabot Test Methods (CTM) based on international Standards

Quoted test results should not be used for specification purposes but are typical test values intended for guidance only.

PACKAGING

PLASBLAK® PE2272 is supplied in regular pellet form packed in 25 kg bags. It should be stored in a dry place. PLASBLAK® PE2272 can also be supplied in micropulverized form under code PM2272. Recommended storage life: up to 1 year provided it is stored as directed.

22-10-2010

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and CABOT DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AS TO (i) SUCH INFORMATION, (ii) ANY PRODUCT OR (iii) INTELLECTUAL PROPERTY INFRINGEMENT. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.

HEAD OFFICE Cabot SCCC Interleuvenlaan 15 I B - 3001 Leuven - Belgium Tel : +32 16 39 24 00 Fax : +32 16 39 24 44	Cabot Plastics Belgium S.A. Rue Prevochamps 78 B - 4860 Pepinster - Belgium Tel: +32 87 39 27 11 Fax: +32 87 46 98 69	Cabot Plastics Deutschland Tel: (0800) 182 40 86 Fax: (0800) 182 40 87 c/o Cabot Plastics Belgium S.A. (see address on the left)	中国 卡博特(中国)投资有限公司 中国上海吴淞双柏路558号 邮编: 201108 电话: +86 21 6434-7766 传真: +86 21 6434-5532
SALES OFFICES Cabot Plastics Hong Kong Ltd 18 Dai Kwai Street Tai Po Industrial Estate / NT Hong Kong SAR - PRC Tel: +852 2666 2666 Fax: +852 2666 0807	Cabot Latin America Division Rua do Paraíso, 148 – 5th floor Paraíso CEP 04103-000 São Paulo SP - Brazil Tel: +55 11 21 44 64 00 Fax: +55 11 32 53 00 51 Tel.: (0800) 195 959 (Customer Service)	Cabot Italiana S.p.A Zona Industriale, 4 I - 38055 Grigno (TN) - Italia Tel: +39 0461 775 211 Fax: +39 0461 765 146	

PLASBLAK®, PLASWITE®, PLASGREY®, PLASADD®, CABELECC® and CABOT® are registered trademarks of Cabot Corporation
© Cabot Corporation, MA, U.S.A. All rights reserved. 2010