

**BLACK PE MASTERBATCH FOR FILM,  
EXTRUSION & MOULDING APPLICATIONS  
REQUIRING SUPERIOR PIGMENTATION & UV  
PROTECTION**



## **PLASBLAK® PE2727**



PLASBLAK® **PE2727** is a polyethylene based black masterbatch designed for use in film, extrusion and moulding applications. It is particularly recommended for co-extruded and thin films requiring high opacity as well as good resistance to UV. It is also recommended for use in construction pipes, tape, netting and geogrid applications. It exhibits optimum carbon black dispersion characteristics together with good dilutability and gives maximum protection against UV light degradation. This product is suitable for use in a wide range of plastics that come into contact with food. For more details regarding the food contact compliance in various European countries, please refer to the relevant Food Contact Statement that you can obtain through your usual Cabot representative.

### **METHOD OF ADDITION**

PLASBLAK® **PE2727** is designed for ease of dilution and homogeneous mixing and is therefore suitable for direct addition using automatic dosing units or by pre-blending.

### **ADDITION RATE**

The amount of masterbatch added depends on the performance requirements of the final application. Typical addition rates vary from 4% to 10% masterbatch (1% to 3% in injection moulding). The recommended addition rate for maximum UV light protection is 6.25% masterbatch in moulding.



**Cabot Corporation**

[www.cabot-corp.com/plastics](http://www.cabot-corp.com/plastics)

# PLASBLAK® PE2727

BLACK PE MASTERBATCH FOR FILM,  
EXTRUSION & MOULDING  
APPLICATIONS REQUIRING  
SUPERIOR PIGMENTATION & UV  
PROTECTION



## PHYSICAL PROPERTIES

PROPERTY	VALUE	TEST METHOD (*)
Carrier	polyethylene	
Pigment	40% weathering carbon black	
Compatibility	LDPE, LLDPE, HDPE, PP, ethylene copolymers	
Density @ 23°C	1140 kg/m3	CTM E023
MFI 21.6 kg/190°C	41 g/10 min	CTM E005 (ISO 1133)

(\*) Tests are performed according to Cabot Test Methods (CTM) based on international Standards

Quoted test results should not be used for specification purposes but are typical test values intended for guidance only.

## PACKAGING

PLASBLAK® PE2727 is supplied in regular pellet form packed in 25 kg bags. It should be stored in a dry place. Recommended storage life: up to 1 year provided it is stored as directed.

12-05-2010

This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and CABOT DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AS TO (i) SUCH INFORMATION, (ii) ANY PRODUCT OR (iii) INTELLECTUAL PROPERTY INFRINGEMENT. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.

<b>HEAD OFFICE</b> Cabot SCCC Interleuvenlaan 15 I B - 3001 Leuven - Belgium Tel : +32 16 39 24 00 Fax : +32 16 39 24 44	<b>Cabot Plastics Belgium S.A.</b> Rue Prevochamps 78 B - 4860 Pepinster - Belgium Tel: +32 87 39 27 11 Fax: +32 87 46 98 69	<b>Cabot Plastics Deutschland</b> Tel: (0800) 182 40 86 Fax: (0800) 182 40 87 c/o Cabot Plastics Belgium S.A. (see address on the left)	<b>中国</b> 卡博特(中国)投资有限公司 中国上海吴泾双柏路558号 邮编:201108 电话: +86 21 6434-7766 传真: +86 21 6434-5532
<b>SALES OFFICES</b> Cabot Plastics Hong Kong Ltd 18 Dai Kwai Street Tai Po Industrial Estate / NT Hong Kong SAR - PRC Tel: +852 2666 2666 Fax: +852 2666 0807	<b>Cabot Latin America Division</b> Rua do Paraíso, 148 – 5th floor Paraíso CEP 04103-000 São Paulo SP - Brazil Tel: +55 11 21 44 64 00 Fax: +55 11 32 53 00 51 Tel.: (0800) 195 959 (Customer Service)	<b>Cabot Italiana S.p.A</b> Zona Industriale, 4 I - 38055 Grigno (TN) - Italia Tel: +39 0461 775 211 Fax: +39 0461 765 146	

PLASBLAK®, PLASWITE®, PLASGREY®, PLASADD®, CABELEC® and CABOT® are registered trademarks of Cabot Corporation  
© Cabot Corporation, MA, U.S.A. All rights reserved. 2010